

GREASES >>>

	9000 Ultra EP	9010 Multi Purpose	9020 Multi Purpose	9030 Crystal	9040 Food Machinery	9050 HD Equipment	9055 Polysyn 555	9060 Moly EP	9090 No-Melt Bentone
NLGI Grade	2	1	2	2	2	2	2	2	2
Penetration @ 77° F, ASTM Worked	280	315-335	270-290	270-290	280	280	270-290	270-290	270-290
Dropping Point (° F)	550	340	345	NONE	550	550	NONE	360	NONE
Base Oil Viscosity cSt @ 40° C	227	227	227	66	NA	460	66	227	475
cSt @ 100° C	15,0	15,0	15,0	9,8	NA	19,0	8,7	15,0	31,0
Molybdenum Disulfite, wt. %	NA	NA	NA	NA	NA	5,0	NA	1,0	NA
Timken OK Load	60	NA	NA	NA	NA	70	70	40	NA
4 Ball Test, ASTM D2266 10 kg 1800 rpm, 75° C, 1 hr	0,28	NA	NA	NA	NA	NA	NA	NA	NA
40 kg 1200 rpm, 75° C, 1 hr	0,45	NA	NA	NA	0,75	0,44	NA	NA	NA
4 Ball Load, ASTM D2596, kg	400	NA	NA	NA	250	800	NA	NA	NA
Load Wear Index	NA	NA	NA	NA	NA	147,4	NA	NA	NA
Water Washout, wt. %	NA	NA	NA	NA	2,5	2	NA	NA	NA
Oil Separation, wt. %	NA	NA	NA	NA	1,7	3	NA	NA	NA
Soap Type	LI COM	LI 12-HS	LI 12-HS	SIA	AL COM	LI COM	SIA	LI 12-HS	None
Color	Purple	Amber	Amber	Clear	White	Dark Grey	Red	Dark Grey	Amber
Appearance	Buttery	Buttery	Buttery	Tacky	Smooth	Smooth	Buttery	Buttery	Buttery
Rust Test, ASTM D1743	Pass	NA	NA	NA	NA	NA	NA	NA	NA
Corrosion Test, ASTM D4048	Pass	NA	NA	NA	NA	NA	NA	NA	NA
Available package size	400 g tubes								

NA Not available
LI COM Lithium Complex
LI 12-HS Lithium 12 - Hydroxy Stearate

AL COM Aluminium Complex
SIA Synthetic Inorganic Gel Agent